




EUROPEAN PATENT APPLICATION

 Application number: 84304544.4


 Int. Cl.⁴: C 12 P 19/04
 C 12 N 1/20, C 08 B 37/00

 Date of filing: 03.07.84


 Priority: 07.07.83 GB 8318403

 Date of publication of application:
 20.03.85 Bulletin 85/12


 Designated Contracting States:
 DE FR GB

 Applicant: NATIONAL RESEARCH DEVELOPMENT
 CORPORATION
 101 Newington Causeway
 London SE1 6BU(GB)

 Inventor: Sutherland, Ian Wishart
 61 Alnwickhill Road
 Edinburgh EH16 6NJ Scotland(GB)

 Representative: Percy, Richard Keith
 Patent Department National Research Development
 Corporation 101 Newington Causeway
 London SE1 6BU(GB)

 Gel-forming polysaccharides.

 The invention provides a polysaccharide which under-
 goes cation-induced gelation to form gels of useful strength
 at relatively low concentration of cation, and which melt and
 set sharply and reversibly. It has a marked preference in
 terms of gel strength for cations of sodium rather than other
 group Ia elements and calcium rather than other Group IIa
 elements. It contains D-glucose, L-fucose and D-glucuronate
 residues in the approximate molar ratio of 3:1:1. The
 polysaccharide can be isolated from the bacterium NCIB
 11870. Its gels are useful in food and medicine for addition to
 a variety of foodstuffs and pharmaceuticals. They can be
 prepared simply by adding the appropriate cations to a dilute
 aqueous solution of the polymer at ambient temperature,
 whereupon the gel forms rapidly. If desired the gel initially
 formed can be melted and re-set.

GEL-FORMING POLYSACCHARIDES

This invention relates to gel-forming polysaccharides.

- Although an increasing number of microbial polysaccharides have been examined for potentially useful physical properties, relatively few appear to be capable of gel formation. One
- 05 exception is curdlan, a 1,3-linked beta-D-glucan synthesised by Agrobacterium spp. and by Rhizobium meliloti, T. Harada in "Polysaccharides in Food", eds. J.M.V. Blanshard and J.M. Mitchell, Butterworths, London, p. 283 (1979); and T. Harada and A. Amemura, Mem. Inst. Sci. Ind. Res. Osaka Univ. 38, 37, (1981). Another
- 10 gel-forming polymer is an acetylated heteropolysaccharide from Pseudomonas elodes containing glucose, rhamnose and uronic acid in the approximate ratio 2:3:1, I.W. Cottrell, American Chemical Society Symposium series 126 252, (1980); R. Moorhouse et al., ib id, 150, 111 (1981); and K.S. Kang et al., Appln. env.
- 15 Microbiol. 43, 1086 (1982). This material was unusual in that aqueous solutions, after heating and cooling, formed a weak and very elastic gel. Following deacetylation at pH 10.0, the polysaccharide forms firm non-elastic brittle gels with a melting point of 90°C.
- 20 A microbial polysaccharide has now been isolated as an extracellular product of a Gram-negative bacterium and has unusual and potentially valuable gelation behaviour. The newly isolated polysaccharide shows unusual gelation properties of potential technological significance. It contains D-glucose, L-fucose and
- 25 D-glucuronate residues in the approximate molar ratio 3:1:1. No significant amounts of acetate or pyruvate were detected. D-Glucuronate and some D-glucose are destroyed on periodate oxidation, but L-fucose and some D-glucose can be recovered intact, indicating the presence of some 1,3-linkages in the primary structure.
- 30 The major oligosaccharide isolated from auto-hydrolysates was an aldobiuronic acid containing equal amounts of D-glucuronic acid and L-fucose.

Thermally-reversible gels, i.e. which melt and set reversibly, are formed on addition of salts to solutions of the polysaccharide.

Divalent cations are in general more effective than monovalent in promoting gelation of the polysaccharide, while trivalent cations normally cause precipitation. Among cations of Groups Ia and IIa of the Periodic Table, optimum gel strength is achieved with Na⁺ and Ca⁺ (ionic radius about 0.1 nm), larger and smaller ions becoming progressively less effective. Both gel strength and melting temperature increase with increasing salt concentration.

The polysaccharide forms gels of reasonable strength at concentrations of the polysaccharide, which are unusually low, matched only by the expensive polysaccharide agar. For example, gels comparable to those required for normal industrial or food applications may be obtained using a 0.3% w/v aqueous solution of the polysaccharide and 1% w/v sodium chloride solution (about 0.2 M). Gel strength increases with increasing polymer concentration but there is no systematic variation in melting point with polymer concentration. The gel-sol, i.e. the melting, transition of the polysaccharide is unusually sharp and, by suitable adjustment of salt concentration, can be made to occur just below body temperature (e.g. 30-35°), and the gel is therefore useful in biomedical or food applications. An example of a biomedical use is as the vehicle for a gel, cream or lotion.

Two well known gelling polysaccharides are the glycuronans, pectic and alginic acid. They are composed solely of hexuronic acid residues; alginic acid contains D-mannuronic acid and L-guluronic acid and all linkages are 1,4; pectic acid contains D-galacturonic acid. Other gelling compositions are agar and carrageenan. Agar contains D-galactose and 3,6-anhydro-L-galactose, with pyruvate ketals and sulphate esters. Carrageenan contains 4 O-substituted D-galactose-2,6 disulphate residues. No microbial polysaccharides containing sulphate have yet been described. Both agar and carrageenan are mixtures of molecular species.

The newly isolated polysaccharide has in common with alginate and pectate that it forms cation-associated gels, but differs from alginate and pectate in that a gel of reasonably high strength can be formed at a lower concentration of the cation. The newly isolated polysaccharide has in common with carrageenan and agar

that its cation-associated gels melt rapidly. It differs from them in that it has a preference (in terms of gel strength) for cations of a particular ionic radius (sodium and calcium) over other ions (of smaller and larger radius) of the same groups (Ia and IIa) of the Periodic Table.

- The present invention comprises the newly isolated polysaccharide and any similar polysaccharides, e.g. which might be obtainable from closely related bacteria, presenting a generally similar distinction over known polysaccharides. Various combinations of some of the chemical and/or physical properties described herein are capable of defining these polysaccharides. According to one important definition of the polysaccharides of the invention:-
- (1) they contain D-glucose, L-fucose and D-glucuronate residues in the approximate molar ratio of 3:1:1;
 - (2) when oxidised by periodate they give a product containing some only of the D-glucose residues of the unoxidised polymer, substantially all the L-fucose residues of the unoxidised polymer and substantially no D-glucuronate;
 - (3) they form gels when cations of at least any one of the elements lithium, sodium, potassium, rubidium and caesium of Group Ia of the Periodic Table and magnesium, calcium, strontium and barium of Group IIa of the Periodic Table are added to an aqueous solution of the polymer;
 - (4) the gels thus formed melt on heating and set on cooling reversibly;
 - (5) the strength of the gels increases with increasing concentration of the polymer in aqueous solution;
 - (6) the polymers form stronger gels with Group Ia and IIa cations of a particular ionic radius than with other Group Ia and IIa cations; and
 - (7) they are obtainable by isolation from the bacterium NCIB 11870 as defined hereinafter, or a variant or mutant thereof.

Optionally the polysaccharide can be further characterised in that the gel formed by addition of 0.17 M aqueous sodium chloride solution to a 0.3% w/v (g/100 ml) aqueous solution of the polymer

at ambient temperature has a yield stress at 25°C of the order of at least 10 g.cm⁻².

The newly isolated polysaccharide of the invention is obtainable by culturing the bacterium NCIB 11870, which has been deposited as
05 a patent deposit at the National Collection of Industrial Bacteria, c/o The National Collections of Marine and Industrial Bacteria Ltd., Torry Research Station, P O Box 31, 135 Abbey Road, Aberdeen, Scotland AB9 8DG on 10 June 1983 under the above Accession Number. The bacterial strain was isolated in the laboratory from a carbo-
10 hydrate-rich environment. It is Gram-negative and takes the form of rods, approximately 2-3 micrometres x 1 micrometre. It is non-motile. It grows well in nutrient broth, Davis/Mingioli and other relatively simple media, growth being assisted by the presence of small quantities of yeast extract or casein hydrolysate. It
15 forms colonies after about six days on Davis/Mingioli or similar media. The colonies are of diameter 4-5 mm, grey-white translucent, circular, convex and extremely viscous leading to trails of polymer from a needle inserted into such colonies. Growth is optimum at or near 35°C, poor at temperatures above 39°C or below 10°C. The
20 bacterium is a facultative anaerobe, but is best grown aerobically. Results of standard tests are: oxidase negative; methyl red negative; Voges-Proskauer positive; citrate utilised; fermentation of D-glucose, D-fructose, D-mannose, D-xylose, D-galactose, D-mannitol, sucrose and trehalose, in all cases with production of
25 acid and gas; starch hydrolysis negative. It produces the polysaccharide of the invention on media containing an acceptable carbon source, for example glucose or sucrose, D-Fructose, D-mannose, or glutamic acid could be used but is less preferred. The bacterial strain has been tentatively assigned to the
30 Enterobacter species.

The invention includes the bacterium NCIB 11870 as defined by the deposit details given above, variants and mutants thereof. It also includes a biologically pure culture thereof. It includes a method of preparing the newly isolated polysaccharide of the
35 invention which comprises culturing NCIB 11870 at a temperature

from 10 to 39°C with a source of assimilible carbon and separating the polysaccharide thereby produced extracellularly.

Although the newly isolated polysaccharide of the invention is defined inter alia as obtainable from NCIB 11870, it must be
05 emphasised that such definition is not intended to limit the polysaccharide to one actually obtained from such a bacterium (and still less from the particular sample thereof deposited at the NCIB). In other words, the "obtainable by" element of
10 the definition is included merely because of the difficulty of formulating a full chemical definition and to aid in identifying the polysaccharide. Thus the same polysaccharide (or, as explained above, any similar one) produced partially or wholly by chemical synthesis or by recombinant DNA technology or by bacterial synthesis
15 from a different culture, strain, species, or even genus of micro-organism is not excluded from the ambit of the present invention.

Besides the polysaccharides themselves the invention includes a gellable aqueous composition (which may be a solution or a sol) containing a polysaccharide of the invention and a gel-forming
cation, which is normally of Group Ia (lithium to rubidium) or IIa
20 (beryllium or barium) of the Periodic Table, although other cations are not excluded. Ammonium (NH_4^+) is an example of such another cation. Sodium and calcium are preferred for gelling the newly isolated polysaccharide, i.e. the specific embodiment product of
the invention. Any anion can be supplied e.g. chloride or
25 hydroxide. The gel and the process of gelation by setting the gellable composition, preferably by allowing it to set at ambient temperature, or if necessary upon heating or cooling, are also part of the present invention.

The resulting gels are thermally reversible and show sharp
30 melting and setting behaviour. More homogeneous and cohesive gels may be obtained by melting the gel formed initially at room temperature and allowing it to reform on cooling, or by mixing polymer and salt solutions at a temperature above the melting point of the final gel.

35 The ionic concentration required varies widely for different salts and, in common with other gelling polymers, a minimum critical

concentration of the polysaccharide is required for gel formation. In general, gels of comparable strength to those normally used for typical industrial or food applications may be obtained at a polymer concentration of about 0.3%, i.e. somewhat higher than for agar, but appreciably lower than for carrageenan, alginate, gelatin or starch.

Hereinafter the invention is described and illustrated by reference to the newly isolated polysaccharide which for convenience is called simply the "polysaccharide" or the "polymer". Concentrations of polysaccharide in w/v are metric, i.e. g/ml. All other percentages are by weight unless the context implies otherwise.

The following Table shows properties of gels of the invention obtained by adding various salts as shown to aqueous solutions of the polysaccharide, as shown. Divalent cations are in general more effective than monovalent in the gelation, while trivalent cations normally cause the polymer to precipitate. Cohesive gels were, however, obtained with Fe^{3+} ions over the concentration range 0.30-0.34 mM.

Table: Properties of gel of the invention

Polymer % w/v	Salt	Salt conc. (mM)	Melting temperature (°C)	Gel strength (g.cm ⁻²)
0.1	NaCl	170	30	-
0.1		509	40	1.3
0.2		170	33	2.8
0.2		509	45	7.7
0.3		170	30	11.3
0.3		509	45	15.1
0.1	KCl	133	33	1.1
0.1		400	40	2.85
0.2		133	30	-
0.2		400	45	7.3
0.3		133	30	6.4
0.3		400	45	16.8

Table: Properties of gel of the invention (Cont'd)

Polymer % w/v	Salt	Salt conc. (mM)	Melting temperature (°C)	Gel strength (g.cm. ⁻²)
0.1	CaCl	178	30	-
0.2		178	33	6.4
0.3		178	33	5.6
0.1	LiCl	235	30	-
0.1		706	30	1.4
0.2		235	30	1.4
0.2		706	40	4.8
0.3		706	45	10.2
0.1	NH ₄ Cl	190	30	0.6
0.1		571	33	0.95
0.2		190	37	2.3
0.2		571	45	5.2
0.3		190	30	10.7
0.3		571	45	15.5
0.1	MgCl ₂	49	30	0.7
0.1		148	30	1.7
0.2		49	33	3.4
0.2		148	33	5.7
0.3		49	33	11.2
0.3		148	45	13.9
0.3	SrCl ₂	31	33	4.6
0.3		63	40	11.6
0.3		188	45	10.6

Table: Properties of gel of the invention (Cont'd)

Polymer % w/v	Salt	Salt conc. (mM)	Melting temperature (°C)	Gel strength (g.cm ⁻²)
0.05	CaCl ₂	202	33	0.5
0.1		67	40	1.3
0.1		202	45	3.5
0.2		67	40	7.0
0.2		202	45	8.0
0.3		67	33	12.1
0.3		335	40	13.9
0.3		67	45	15.6
0.3		202	45	16.6

In the Example hereinafter which illustrates the invention, reference is made to the accompanying drawings, in which:-

Figure 1 is a graph showing the variation in gel strength (yield stress; 25°C) of polysaccharide (0.3 w/v) with cation concentration, the cations shown (chloride salt form) being Na⁺ (▲), K⁺ (○), NH₄⁺ (◻), Mg²⁺ (△), Ca²⁺ (●) and Sr²⁺ (●);

Figure 2 is a graph showing molar concentrations of different cations (chloride salt form) required to produce gels (0.3 w/v polysaccharide; 25°C) of the same strength (a yield stress of 10.9 g.cm⁻²), the concentration being plotted against ionic radius;

Figure 3a and 3b are graphs of polymer concentration against gel strength (yield stress; 25°C), as follows:-

(3a) : Na⁺ concentrations of 170 (■) and 500 (●) mM (1% and 3% NaCl, respectively).

(3b) : Ca²⁺ concentrations of 67 (■) and 200 (●) mM (1% and 3% CaCl₂.2H₂O, respectively);

Figure 4 contains two graphs, in which the gel-sol transition (0.3 w/v; 0.2 M NaCl) is monitored by plotting the temperature against rigidity modulus G' (●) and optical rotation (○) ,

Figure 5 contains two graphs in which the gel-sol transition of the polysaccharide (0.3 w/v in D₂O; 0.2 M NaCl) is monitored by loss of detectable high-resolution n.m.r. signal (circles) and by optical rotation (triangles); filled symbols show results obtained on heating and open symbols results obtained on cooling;

Figure 6 is a plot of circular dichroism (theta) of the polysaccharide (0.3 w/v; 0.2 M NaCl) at 43 (o), 31 (●), 28 (◐), 25 (◑), 22 (Δ) and 13 (▲) °C against wavelength.

Sugar ratios in the native and periodate-oxidized polymer were determined by alditol acetate analysis on a Pye 104 chromatograph, using columns of 3% SP-2340 on 100/120 Supelcoport, or OV 225. Uronic acid was determined by the method of N. Blumenkrantz and G. Asboe-Hansen, *Anal. Biochem.* 54, 184 (1973). Gels were prepared by addition of an appropriate salt solution to an aqueous solution to the polymer, heating to about 45°C to melt the initial gel, and re-cooling. Solutions for optical studies were clarified by filtration through a 0.45 micrometre "Millipore" membrane.

Gel strength (yield stress) was determined using a simple penetrometer. Rigidity modulus was measured on a Rheometrics Mechanical Spectrometer (RMS-605) using the standard transducer with a 50 mm diameter cone and plate of cone angle 0.04 rad. Measurement was at 10 rad. s⁻¹ and 10% strain, using a heating rate of 1 degree/min for increasing the temperature of measurement. Solution viscosity measurements were made on a Ferranti cone and plate viscometer. Optical rotation was measured at 436 nm in a 10 cm pathlength cell on a Perkin Elmer 245 polarimeter, and circular dichroism spectra were recorded on a Jobin-Yvon Dichrograph Mk. V, using a 0.2 mm pathlength cell. In both cases, temperature was controlled by circulating water bath and monitored by a thermocouple within the cell, but out of the light path. High resolution proton n.m.r. measurements were made at 300 MHz on Bruker CXP 300 Fourier transform spectrometer. Peak areas were quantified relative to a standard pyrazine solution contained in a 2 mm-diameter capillary located centrally within the n.m.r. tube.

EXAMPLE

The bacterial strain NCIB 11870, as obtained in freeze-dried form, was plated out nutrient agar, MacConkey's agar or semi-synthetic medium containing glucose and yeast extracts. The polysaccharide was then prepared by culturing the bacterium on the same semi-synthetic medium using a 500 ml portion thereof shaken in a 2 litre Erlenmeyer flask. The polysaccharide was then recovered from the culture supernatant by precipitation with acetone or ethanol.

Hydrolysates of the polysaccharide (1 M trifluoroacetic acid at 100°C for 16 hours) gave material chromatographically identical with glucose, fucose and glucuronic acid. Preparation of alditol acetates confirmed the identity of the neutral sugars and the colour development in the procedure of N. Blumenkrantz and G. Asboe-Hansen, supra, confirmed the presence of uronic acid. The molar ratio of sugar components L-fucose: D-glucose: D-glucuronate of the polysaccharide was 1:3.3:1.06. After periodate oxidation the D-glucuronate was destroyed and the L-fucose: D-glucose molar ratio was 1:1.96. The D-configuration of the glucose residues was confirmed by glucose oxidase. No significant amounts of O-acetyl groups or pyruvate ketal were detected.

Attempts to obtain oligosaccharides by partial acid hydrolysis were largely unsuccessful. However, autohydrolysis of a 0.5% (w/v) solution of the acid form of the polymer yielded one major oligosaccharide product. This proved to be an aldobiuronic acid, which on hydrolysis yielded equal quantities of fucose and glucuronic acid. Other oligosaccharides, obtained in smaller yield from the autohydrolysis were a trisaccharide containing approximately equimolar amounts of fucose, glucuronic acid and glucose and a tetrasaccharide in which the same three monosaccharides were present in the approximate molar ratio of 1:1:2. One neutral disaccharide containing D-glucose only was obtained.

The strength (yield stress) of the gels of the invention formed at 0.3% w/v polymer concentration is shown in Figure 1 for

different concentrations of various cations (chloride salt form). In all cases, gel strength increases with increasing salt concentration.

05 There is considerable selectivity between different cations of the same valency. Figure 2 shows the molar concentrations of Group Ia and Group IIa cations required to produce gels of the same strength, using a fixed concentration (0.3% w/v) of polymer. In both cases, optimum gelation is obtained at an ionic radius of about 0.1 nm (Na^+ and Ca^{2+} respectively), with higher concentra-
10 tions being required for both larger and smaller cations.

The minimum critical concentration of the polymer necessary for gelation also varies with the cation used (see Table above). For example, at the lower polysaccharide concentration tested (0.05% w/v) a gel was formed only with Ca^{2+} . At concen-
15 trations above the minimum required for gelation, gel strength increases with increasing polymer concentrations, as illustrated in Figure 3.

The melting temperature of the polysaccharide gels shows little, if any, systematic variation with polymer concentration,
20 but increases appreciably with increasing ionic strength (see Table above). Similar behaviour is well-known for other charged polysaccharides and can be attributed to suppression of electrostatic repulsion, thus facilitating interchain association and network formation.

25 The thermally-induced gel-sol transition of the polysaccharide is accompanied by a sharp change in optical rotation, with a closely similar temperature course (Figure 4) to the loss of gel structure, as monitored by rigidity modulus (G'). Polysaccharide optical rotation is sensitive to chain geometry and an abrupt change
30 of this type is indicative of a co-operative conformational transition, T.A. Bryce *et al.*, Faraday Discuss. Chem. Soc. 57, 221 (1974). For example, the thermally-induced order-disorder transitions of agarose, S. Arnott, *et al.*, J. Mol. Biol. 90, 269 (1974); carrageenan, A.A. McKinnon *et al.*, Chem. Commun., 701 (1969);
35 E.R. Morris *et al.*, J. Mol. Biol. 138, 349 (1980) and xanthan,

D.A. Rees, *Biochem. J.* 126, 257 (1972), G. Holzwarth *Biochemistry* 15, 4333 (1976); E.R. Morris *et al.*, *J. Mol. Biol.* 110, 1 (1977); and M. Milas and M. Rinaudo, *Carbohydr. Res.* 76, 189 (1979); all give optical rotation-temperature profiles similar to that shown in Figure 4. In comparison with these other polymers, however, the transition of the polysaccharide of the invention is usually sharp, suggesting a highly co-operative process between cation and polymer.

As shown in Figure 5 the conformation transition indicated by optical rotation is accompanied by a progressive loss of detectable high resolution n.m.r. signal on cooling, as expected for adoption of a conformationally rigid, ordered structure. The changes in both optical rotation and n.m.r. are fully reversible (Figure 5), with no detectable thermal hysteresis.

Figure 6 shows the circular dichroism (c.d.) of the polysaccharide over a range of temperatures (13-43°C) spanning the sol-gel transition. The spectra are similar to those reported by E.R. Morris *et al.*, *J. Chem. Soc. Trans. Perkin II*, 1418 (1975) for the carboxyl $\alpha \longrightarrow \beta$ transition of uronic acid glycosides, consistent with the presence of glucuronosyl residues in the primary structure of the polysaccharide. The negative sign of the observed c.d. band confirms the β configuration of these residues. Since neutral sugars such as glucose and fucose have no electronic transitions over the wavelength range shown in Figure 6 and acetate and/or pyruvate substituents are present in negligible amounts, if at all, observed c.d. intensities may be expressed as molar ellipticity (theta) per glucuronate residue (Figure 6 - right hand axis) using the polysaccharide composition data given hereinbefore.

The sol-gel transition of the polysaccharide is accompanied by an appreciable enhancement of c.d. intensity which follows the same temperature course as the change in optical rotation at higher wavelengths. The c.d. change between the sol and gel states is similar in form to the spectral changes observed on Ca^{2+} -induced gelation of alginate or pectate and centred at the same wavelength (about 208 nm), although of somewhat greater magnitude.

05 The direction of c.d. change (to more negative values) for the D-glucuronate residues is the same as that for D-galacturonate in pectin, and opposite to that observed for L-guluronate residues of alginate (as expected for near mirror-image molecules experiencing the same perturbation). These close similarities in c.d. behaviour suggest that the underlying molecular process causing the c.d. change may also be similar in all three cases, i.e. specific site-binding of cations in close proximity to the carboxy chromophores.

10 The spectroscopic studies above indicate that gelation occurs by formation of extended, co-operative junction zones in which the participating chains are locked in a regular, ordered conformation, while on thermal melting the polymer reverts to the disordered ("random coil") state. The order-disorder transition is usually
15 sharp, indicating a high degree of co-operativity. The absence of any detectable thermal hysteresis further suggests that interchain association is limited to the formation of ordered junctions involving a small, finite number of chains, rather than large aggregates as in the case of, for example, agarose.

20 The marked selectivity for cations of a particular ionic radius (Figure 2) indicates specific incorporation of cations of the most appropriate size within the ordered structure, as in the "egg-box" binding of divalent cations in alginate and pectate gels, rather than non-specific "condensation" of ions along the
25 polymer chain. The large, characteristic changes in carboxyl circular dichroism spectrum which accompany the sol-gel transition (Figure 6) lend further support to this interpretation. These changes follow the same temperature course as the disorder-order transition the polymer chain (as measured by change in optical
30 rotation), indicating that cation binding is an integral part of the ordering process, rather than occurring as a separate event.

CLAIMS

1. A polysaccharide characterised in that
 - (1) it contains D-glucose, L-fucose and D-glucuronate residues in the approximate molar ratio of 3:1:1;
 - 05 (2) when oxidised by periodate it gives a product containing some only of the D-glucose residues of the unoxidised polymer, substantially all the L-fucose residues of the unoxidised polymer and substantially no D-glucuronate;
 - (3) it forms gels when cations of at least any one of the elements lithium, sodium, potassium, rubidium and caesium of Group Ia of the Periodic Table and magnesium, calcium, 10 strontium and barium of Group IIa of the Periodic Table are added to an aqueous solution of the polymer;
 - (4) the gels thus formed melt on heating and set on cooling reversibly;
 - 15 (5) the strength of the gels increases with increasing concentration of the polymer in aqueous solution;
 - (6) the polymer forms stronger gels with Group Ia and IIa cations of a particular ionic radius than with other Group Ia and IIa cations; and
 - 20 (7) the polymer is obtainable by isolation from the bacterium NCIB 11870 deposited as a patent deposit at the National Collection of Industrial Bacteria, Torry Research Station, P O Box 31, 135 Abbey Road, Aberdeen, Scotland AB9 8DG on 10 June 1983 or from a variant or mutant thereof.
- 25 2. A polysaccharide according to Claim 1 further characterised in that in item (6) of the definition the cations of Group Ia and IIa of a particular ionic radius are sodium or calcium ions.
3. A polysaccharide according to Claim 1 or 2 further characterised in that the gel formed by addition of 0.17 M aqueous 30 sodium chloride solution to a 0.3% w/v (g/100 ml) aqueous solution of the polymer at ambient temperature has a yield stress at 25°C of at least 10 g/cm².
4. The bacterium NCIB 11870 deposited in the manner set forth in Claim 1 and variants and mutants thereof.

5. A biologically pure culture of a bacterium defined in Claim 4.
6. A gel comprising a polysaccharide defined in Claim 1, 2 or 3 and a gel-forming cation therefor.
7. A gel according to Claim 6 wherein the ratio of cation to polymer is selected to impart to the gel the property of melting at or just below human body temperature.
- 05 8. A gellable aqueous composition containing a polysaccharide defined in Claim 1, 2 or 3 and a gel-forming cation.
9. A method of preparing a gel claimed in Claim 6 or 7 which
- 10 comprises setting a gellable composition defined in Claim 8.
10. A method according to Claim 9 wherein the gel is set at ambient temperature.




Fig. 1.




Fig.2.




Fig. 3a.




Fig. 3b.




Fig. 4.




Fig. 5.




Fig.6.



European Patent Office

Application number: 84304544.4

0134649

**DECLARATION PURSUANT TO RULE 28, PARAGRAPH 4,
OF THE EUROPEAN PATENT CONVENTION**

The applicant has informed the European Patent Office that, until the publication of the mention of the grant of the European patent or until the date on which the application has been refused or withdrawn or is deemed to be withdrawn, the availability of the micro-organism(s) identified below, referred to in paragraph 3 of Rule 28 of the European Patent Convention, shall be effected only by the issue of a sample to an expert.

IDENTIFICATION OF THE MICRO-ORGANISMS

Accession numbers of the deposits:

NCIB 11870

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

☐ BLACK BORDERS

☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES

☐ FADED TEXT OR DRAWING

☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING

☐ SKEWED/SLANTED IMAGES

☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS

☐ GRAY SCALE DOCUMENTS

☐ LINES OR MARKS ON ORIGINAL DOCUMENT

☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY

☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.